



Pochette Nylon Classe 100 avec ZIP – Lot de 500

- Code Article : [DP51964N001](#)

Spécifications :

Property	Nonminal Value	Test Method
Density	0.92 g/cm ³	ASTM D1505
Tensile Strength	MD >2200 psi	ASTM D882
	TD >2200 psi	ASTM D882
Tensile Elongation	MD 300%	ASTM D882
	TD 350%	ASTM D882
Seal strength	>30N	ASTM F88
Puncture resistance	>6 lbs	MIL STD 3010-2065
MVTR	0.15gm/100in ² /24 hours	ASTM F1249

- Manufactured in ISO Class 5 cleanroom
- Components of animal origin have not been knowingly added to this product
- Slip agent is not used in this product
- This product is not manufactured with any of the Substances on Very High Concern (SVHC)
- This product is REACH compliant
- Complies with California Proposition 65
- 21 CFR177.1520(c), paragraph 2.2 compliant
- European Commission (EU) No 10/2011 compliant as of 4/9/2012
- Complies with the requirements of Article 4.1 of EU Directive 2011/65/EU (RoHS)
- This product is not intentionally manufactured with Bisphenol A, natural rubber, natural la Phthalates, Fluorotelomers, Perfluorooctanoic acid (PFOA) or Perfluorooctane sulfonate (PFO)
- This product is not manufactured with bi-products of crustaceans, eggs, fish, peanuts, soybeans Milk, nuts, celery, mustard, sesame seeds. Sulfur Dioxide or sulfates, lupin or mollusks
- Polyethylene is typically stable during gamma radiation exposure between 25 and 40kgy